

## ABSTRACT

The present invention is directed to a moisture curable, hot melt adhesive coating and/or sealant composition. The composition comprises (a) a first isocyanate-terminated prepolymer comprising the reaction product of an at least essentially semicrystalline hydroxy-functional material (Component A) and a polyisocyanate; (b) a second isocyanate-terminated prepolymer comprising the reaction product of an essentially semicrystalline poly(tetramethylene ether) glycol that has a molecular weight of at least about 1000 (Component B) and a polyisocyanate; and (c) a third isocyanate-terminated prepolymer comprising the reaction product of an essentially amorphous hydroxy-functional material (Component C) and a polyisocyanate, the essentially amorphous hydroxy-functional material having an average functionality less than 2.5 and a  $T_g \leq -20$  °C. All essentially amorphous hydroxy-functional materials in the composition have a  $T_g \leq -20$  °C.

q:\3mupeo forms and samples\patent application basic format.doc